

Technical Data Sheet

Product: CIIR 1338

Description

CIIR 1338 is a synthetic rubber with low Mooney viscosity, a chlorinated copolymer of isobutylene and isoprene.

Application

It is widely used for tire inner-liners, anti-corrosive linings, waterproof materials, anti-vibration products, shoe soles,TPV, etc.

Specifications

Property/Unit	Specification	Test Method
Appearance	White to light yellow solid	Visual
Mooney Viscosity ML (1+8) 125°C (MU)	38.0±4.0	GB/T 1232.1
Chlorine Content (wt%)	1.25±0.10	JingBo Method
Volatiles (wt%)	≤0.5	GB/T 24131.2
Ash Content (wt%)	≤0.5	GB/T 4498.1
Antioxidant (non-Staining) (wt%)	≥0.03	JingBo Method

Curing Characteristics

Property/Unit	Specification	Test Method
FL (dN.m)	2.5±0.8	Compounding method: ASTM D3958 (IRB 9) Test condition: SH/T 1717-2008-6.2 Test method: GB/T 16584
FH (dN.m)	8.0±1.2	
ts1 (min)	1.2±0.8	
T50 (min)	3.0±1.5	
T90 (min)	8.0±2.5	

Packaging

Produced in the form of bales 34 kg each, individually packed in low melting PE/EVA/(EVA+PE) composite film without perforation. Bales packed in wooden box or revolving iron boxes, 36 bales per box.

Safety

Product is a solid polymer with stable performance and is harmless to human beings, animals, plants and ecological environment. See the product MSDS for relevant.

Storage and transportation

The item must be stored in dry and ventilative warehouse and kept out of direct sunlight, moisture and contamination.